

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

|  |           |  |
|--|-----------|--|
| <b>(51) International Patent Classification <sup>6</sup> :</b><br><b>C07D 251/70, C08F 20/68</b>   | <b>A1</b> | <b>(11) International Publication Number:</b> <b>WO 99/05127</b><br><b>(43) International Publication Date:</b> 4 February 1999 (04.02.99)   |
| <b>(21) International Application Number:</b> PCT/GB98/02104<br><b>(22) International Filing Date:</b> 16 July 1998 (16.07.98)<br><br><b>(30) Priority Data:</b><br>9715709.3 26 July 1997 (26.07.97) GB<br><br><b>(71) Applicant (for all designated States except US):</b> THE SECRETARY OF STATE FOR DEFENCE [GB/GB]; Defence Evaluation & Research Agency, Ively Road, Farnborough, Hampshire GU14 0LX (GB).<br><br><b>(72) Inventors; and</b><br><b>(75) Inventors/Applicants (for US only):</b> WILLIS, Colin, Robert [GB/GB]; CBD Porton Down, Salisbury, Wiltshire SP4 0JQ (GB). BREWER, Stuart, Anson [GB/GB]; CBD Porton Down, Salisbury, Wiltshire SP4 0JQ (GB). JONES, Brian, George [GB/GB]; CBD Porton Down, Salisbury, Wiltshire SP4 0JQ (GB).<br><br><b>(74) Agent:</b> BOWDERY, A., O.; D/IPR, Formalities Section, Poplar 2, MOD Abbey Wood #19, Bristol BS34 8JH (GB).  |           | <b>(81) Designated States:</b> AU, CA, CN, GB, JP, KR, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).<br><br><b>Published</b><br><i>With international search report.</i> |
| <b>(54) Title:</b> FLUORINATED TRIAZINE MONOMERS<br><br><b>(57) Abstract</b><br><p>A compound of formula (I), wherein R<sup>1</sup> and R<sup>2</sup> are independently selected from saturated fluorocarbon substituted side chains, such as NR<sup>5</sup>(CH<sub>2</sub>)<sub>n</sub>C<sub>m</sub>F<sub>2m+1</sub>, O(CH<sub>2</sub>)<sub>n</sub>C<sub>m</sub>F<sub>2m+1</sub>, S(CH<sub>2</sub>)<sub>n</sub>C<sub>m</sub>F<sub>2m+1</sub>, NR<sup>5</sup>S(O)<sub>2</sub>(CH<sub>2</sub>)<sub>p</sub>C<sub>m</sub>F<sub>2m+1</sub>, or CR<sup>5</sup>[CO<sub>2</sub>(CH<sub>2</sub>)<sub>n</sub>C<sub>m</sub>F<sub>2m+1</sub>]<sub>2</sub>, where R<sup>5</sup> is hydrogen or alkyl, n and m are independently an integer of 1–12, and p is 0 or an integer of 1–12, R<sup>3</sup> is an unsaturated moiety which may be polymerised, and X is O, S or NR<sup>4</sup> where R<sup>4</sup> is hydrogen or alkyl, as well as methods for the preparation of these compounds. Compounds of formula (I) are useful monomers in the preparation of oil- and water-repellent polymers.</p> <div data-bbox="1050 1565 1605 1870"><p style="text-align: right;">(I)</p></div> |           |  |

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

|    |                          |    |  |    |  |    |                          |
|----|--------------------------|----|--|----|--|----|--------------------------|
| AL | Albania                  | ES | Spain                                    | LS | Lesotho                                      | SI | Slovenia                 |
| AM | Armenia                  | FI | Finland                                  | LT | Lithuania                                    | SK | Slovakia                 |
| AT | Austria                  | FR | France                                   | LU | Luxembourg                                   | SN | Senegal                  |
| AU | Australia                | GA | Gabon                                    | LV | Latvia                                       | SZ | Swaziland                |
| AZ | Azerbaijan               | GB | United Kingdom                           | MC | Monaco                                       | TD | Chad                     |
| BA | Bosnia and Herzegovina   | GE | Georgia                                  | MD | Republic of Moldova                          | TG | Togo                     |
| BB | Barbados                 | GH | Ghana                                    | MG | Madagascar                                   | TJ | Tajikistan               |
| BE | Belgium                  | GN | Guinea                                   | MK | The former Yugoslav<br>Republic of Macedonia | TM | Turkmenistan             |
| BF | Burkina Faso             | GR | Greece                                   | ML | Mali   | TR | Turkey                   |
| BG | Bulgaria                 | HU | Hungary                                  | MN | Mongolia                                     | TT | Trinidad and Tobago      |
| BJ | Benin                    | IE | Ireland                                  | MR | Mauritania                                   | UA | Ukraine                  |
| BR | Brazil                   | IL | Israel                                   | MW | Malawi                                       | UG | Uganda                   |
| BY | Belarus                  | IS | Iceland                                  | MX | Mexico                                       | US | United States of America |
| CA | Canada                   | IT | Italy                                    | NE | Niger  | UZ | Uzbekistan               |
| CF | Central African Republic | JP | Japan                                    | NL | Netherlands                                  | VN | Viet Nam                 |
| CG | Congo                    | KE | Kenya                                    | NO | Norway                                       | YU | Yugoslavia               |
| CH | Switzerland              | KG | Kyrgyzstan                               | NZ | New Zealand                                  | ZW | Zimbabwe                 |
| CI | Côte d'Ivoire            | KP | Democratic People's<br>Republic of Korea | PL | Poland                                       |    |                          |
| CM | Cameroon                 | KR | Republic of Korea                        | PT | Portugal                                     |    |                          |
| CN | China                    | KZ | Kazakstan                                | RO | Romania                                      |    |                          |
| CU | Cuba                     | LC | Saint Lucia                              | RU | Russian Federation                           |    |                          |
| CZ | Czech Republic           | LI | Liechtenstein                            | SD | Sudan  |    |                          |
| DE | Germany                  | LK | Sri Lanka                                | SE | Sweden                                       |    |                          |
| DK | Denmark                  | LR | Liberia                                  | SG | Singapore                                    |    |                          |
| EE | Estonia                  |    |  |    |  |    |                          |

## FLUORINATED TRIAZINE MONOMERS

The present invention relates to novel monomeric compounds which can be used in the production of polymers which have a high degree of oil and water-repellency and which may be fixed to substrates such as clothing, to processes for their preparation and to polymers produced therefrom.

Oil- and water- repellent treatments are in widespread use, in particular for outdoor clothing applications, sportswear, leisurewear and in military applications. These treatments generally require the incorporation of a fluoropolymer into or more particularly, fixed onto the surface of the clothing fabric. The degree of oil and water repellency is a function of the number of fluorocarbon groups or moieties that can be fitted into the available space. The greater the concentration of such moieties, the greater the repellency of the finish.


In addition however, the polymeric compounds must be able to form durable bonds with the substrate. Oil-and water-repellent textile treatments are generally based on fluoropolymers that are applied to fabric in the form of an aqueous emulsion. The fabric remains breathable and permeable to air since the treatment simply coats the fibres with a very thin, liquid-repellent film. In order to make these finishes durable, they are sometimes co-applied with cross-linking resins that bind the fluoropolymer treatment to fibres. Whilst good levels of durability towards laundering and dry-cleaning can be achieved in this way, the cross-linking resins can seriously damage cellulosic fibres and reduce the mechanical strength of the material.

WO 97/13024 discloses a group of fibre reactive polymers, which include a functional group such as a triazine group, which binds the polymer to the material substrate.

- 5 British patent No 1,102,903 describes certain fluoro alkyl containing compounds which are used in water- and oil-repellent compositions.

The applicants have produced certain novel monomers,  
10 which give rise to polymers which have a high number of fluorocarbon substituents per monomer unit.

The present invention provides a compound of formula (I)



(I)

- wherein R<sup>1</sup> and R<sup>2</sup> are independently selected from saturated fluorocarbon substituted side chains;  
20 R<sup>3</sup> is an unsaturated moiety which may be polymerised, and X is O, S or NR<sup>4</sup> where R<sup>4</sup> is hydrogen or alkyl.

As used herein, the term "alkyl" refers to straight or branched chain alkyl or cycloalkyl groups, in particular  
25 those having from 1 to 12 and preferably from 1 to 6 carbon atoms. The term "saturated" refers to groups which do not contain carbon-carbon double bonds. Conversely the term "unsaturated" refers to groups which include carbon-carbon double bonds.

30


Suitable fluorocarbon substituted side chains for R<sup>1</sup> and/or R<sup>2</sup> include groups which are hydrophobic groups

which are able to confer water- and/or oil- repellency on the resultant polymer. In particular  $R^1$  and  $R^2$  are independently selected from  $NR^5(CH_2)_nC_mF_{2m+1}$ ,  $O(CH_2)_nC_mF_{2m+1}$ ,  $S(CH_2)_nC_mF_{2m+1}$ ,  $NR^5S(O)_2(CH_2)_pC_mF_{2m+1}$  or  $CR^5[CO_2(CH_2)_nC_mF_{2m+1}]_2$ , where  $R^5$  is hydrogen or alkyl, and  $n$  and  $m$  are independently an integer of 1-12, and  $p$  is 0 or an integer of from 1-12.

Conveniently  $R^1$  and  $R^2$  are the same. They are preferably selected from  $O(CH_2)_nC_mF_{2m+1}$  or  $NR^5S(O)_2(CH_2)_pC_mF_{2m+1}$ . Suitably  $R^5$  is methyl, ethyl or n-propyl, in particular ethyl. Preferred integers for  $n$  and  $p$  are from 1-3, suitably 2, whilst preferred integers for  $m$  are from 6 to 10, most preferably 8.


Suitable polymerisable groups  $R^3$  are alkenes or alkynes which may also include a functional group such as an acyloxy group. Particularly preferred groups for  $R^3$  are groups of formula  $(CH_2)_qOC(O)C(R^6)CR^7R^8$  where  $q$  is an integer of from 1 to 12, suitably from 1 to 4 and especially 2, and  $R^6$ ,  $R^7$  and  $R^8$  are independently selected from hydrogen or alkyl such as  $C_{1-4}$  alkyl. Preferably  $R^6$ ,  $R^7$  and  $R^8$  are all hydrogen.

Compounds of formula (I) are suitably prepared by reacting a compound of formula (II)



(II)

where  $R^1$  and  $R^2$  are as defined in relation to formula (I) and  $Y$  is a leaving group, with a group of formula (III)



(III)

where X is as defined in relation to formula (I) and  $R^{3'}$   
5 is a group  $R^3$  as defined in relation to formula (I) or a  
precursor group which may be reacted to form a group  $R^3$   
and  $R^a$  is hydrogen or alkyl; and thereafter if necessary  
converting a precursor group  $R^{3'}$  to a group  $R^3$ .

10 Preferably  $R^a$  is hydrogen or a lower alkyl, for example a  
 $C_{1-3}$  alkyl, in particular methyl.

Suitable leaving groups for Y include halogen such as  
fluorine and chlorine, in particular chlorine, or amine  
15 leaving groups such as substituted pyridines for instance  
nicotinic acid or colladine.

The reaction is suitably effected in an organic solvent  
such as tetrahydrofuran (THF), acetone, toluene or  
20 chloroform. It may be effected at temperatures of from  
0 to 200°C, suitably from 25 to 150°C, depending upon the  
precise nature of the reactants and solvents involved.  
Conveniently the reaction may be effected at room  
temperature or under reflux conditions.


25 Preferably the reaction is effected under basic  
conditions. Weak bases may suffice, and in some  
instances, the compound of formula (III) may itself act  
as an acid scavenger and so the use of an excess,  
30 particularly a 2 molar excess of the compound of formula  
(III) will ensure that that the reaction proceeds  
effectively.

Suitable groups  $R^{3'}$  which are precursor groups to  $R^3$  would  
35 be apparent to the skilled person. For example, where  
 $R^3$  is a group  $(CH_2)_qOC(O)C(R^6)CR^7R^8$ , a suitable precursor  
group  $R^{3'}$  would be  $(CH_2)_qOH$ , which can be readily converted

to  $R^3$  by reaction with a suitable acid halide for example an acid chloride of formula  $ClC(O)C(R^6)CR^7R^8$  in the presence of a base, such as a weak base, for example pyridine or a pyridine derivative such as collidine.

- 5 This reaction is suitably effected in an organic solvent such as toluene at elevated temperatures, conveniently at the reflux temperature of the solvent.

Certain compounds of formula (II) are known (see for  
10 example British Patent No. 1,102,903). These compounds can be prepared by reacting a compound of formula (IV)



(IV)

15

where  $R^1$  is as defined in relation to formula (I), Y is as defined in relation to formula (II) and  $Y'$  is a leaving group,  
with a compound of formula (V)

20



where  $R^2$  is as defined in relation to formula (I), in the presence of a base.

25


Suitable bases are those which react with a compound of formula (V) so as to produce a nucleophilic moiety of formula (V')

30



Thus the selection of suitable bases will depend upon the precise nature of the group  $R^2$  and will be readily understood or determinable by the skilled person. For example, where  $R^2$  is a group  $O(CH_2)_n C_m F_{2m+1}$ , strong bases such as alkali metal hydroxides, in particular lithium hydroxide, may be used. Alternatively, where  $R^2$  is a group  $NR^5 S(O)_2 (CH_2)_p C_m F_{2m+1}$ , stronger bases such as alkali metal alkoxides, in particular sodium or potassium methoxide or ethoxide may be used.

Compounds of formula (IV) are suitably prepared by reacting a compound of formula (VI)



(VI)

wherein Y, Y' and Y'' are the same or different leaving groups, with a compound of formula (VII)



where  $R^1$  is as defined in relation to formula (I), in the presence of a base.

Reaction conditions will be generally similar to those described above in relation to the reaction between compounds of formula (IV) and formula (V).

Where compounds of formula (V) and formula (VII) are the same, compounds of formula (II) may be prepared directly in one pot. If necessary, the reaction can be controlled




in a stepwise manner in order to maximise yield of the target compound by controlling the reaction temperature. For example, where  $R^1$  and  $R^2$  are groups of formula  $NR^5S(O)_2(CH_2)_nC_mF_{2m+1}$ , the compound of formula (IV) may be prepared at depressed temperatures, for example at about  $-78^\circ\text{C}$ . Allowing the reaction mixture to warm up to approximately  $0^\circ\text{C}$  will produce a compound of formula (II) after suitable work-up.

Compounds of formula (III), (V), (VI) and (VII) are either known compounds or they can be prepared from known compounds using conventional methods. A preferred compound of formula (VI) is cyanuric chloride.


Compounds of formula (I) may be polymerised or copolymerised using conventional technology, e.g emulsion polymerisation.

Polymers or copolymers including units of formula (VIII)



(VIII)

where  $R^1$ ,  $R^2$  and  $X$  are as defined in relation to formula (I),  $t$  is an integer in excess of 5, and  $R^9$  is a saturated derivative of  $R^3$  as defined in relation to formula (I) form a preferred embodiment of the invention. In particular  $XR^9$  will be a moiety of formula (IX)



(IX)

Suitably the monomers of the invention are copolymerised with a monomer which comprises a fibre reactive moiety  
 5 for example as described in WO 97/13024.

The invention will now be particularly described by way of example.

#### 10 Example 1

##### Step 1

##### Synthesis of 2-chloro-4,6-bis(N-ethylperfluorooctylsulphonamido)-1,3,5-triazine

Metallic sodium (4.08g, 177mmols) was reacted with  
 15 methanol (150mls). N-Ethyl perfluorooctyl sulphonamide (93.28g, 177mmols) was added, and the resulting solution was stirred for 30 minutes. The methanol was removed at the pump (a vacuum pump was required to remove the final traces of solvent). The resulting sticky solid was  
 20 dissolved in acetone (300mls) and cooled to -65°C under argon. Recrystallised cyanuric chloride (16.33g, 88.5mmols) dissolved in acetone (100mls) was added to the reaction mixture dropwise such that the temperature did not rise above -50°C (~1hour). After the addition, the  
 25 reaction mixture was allowed to slowly warm to room temperature (1 hour) and then stirred for a further 3 hours. The precipitated solid was removed by filtration and dried under vacuum. Purification by soxhlet extraction with acetone afforded 61g (56.9%) of a fine white powder.

30

<sup>1</sup>H NMR (CDCl<sub>3</sub>) δ (ppm) 4.20 (2H, q, <sup>3</sup>J<sub>H-H</sub> 6.8 Hz, CH<sub>2</sub>CH<sub>3</sub>), 1.40 (3H, t, <sup>3</sup>J<sub>H-H</sub> 6.8 Hz, CH<sub>2</sub>CH<sub>3</sub>).

$^{13}\text{C}\{^1\text{H}\}$  NMR ( $\text{CDCl}_3$ )  $\delta$  (ppm) 171.3, 165.0 (triazine), 46.3 ( $\text{CH}_2\text{CH}_3$ ), 14.5 ( $\text{CH}_2\text{CH}_3$ ).

5    Step 2

Synthesis of 2-N-{4,6-bis(N-ethylperfluorooctylsulphonamido)-1,3,5-triazin-2-yl}-amino ethanol

A THF solution (85mls) of 2-chloro-4,6-bis(N-ethylperfluorooctylsulphonamido)-1,3,5-triazine (15g, 12.9mmols) and ethanolamine (1.6g, 26.2mmols) were heated under reflux for 1 hour. The hot solution/suspension was filtered and the product was allowed to crystallise overnight to afford 12.8g (83%) of product.

15

$^1\text{H}$  NMR ( $\text{d}_6$  acetone)  $\delta$  (ppm) 4.85 (4H, m,  $\text{NCH}_2\text{CH}_3$ ), 4.38 (2H, t,  $^3J_{\text{H-H}}$  5 Hz,  $\text{CH}_2\text{O}$ ), 4.22 (2H, dt, 5, 5 Hz,  $\text{OCH}_2\text{CH}_2\text{N}$ ), 2.05 (6H, m  $\text{NCH}_2\text{CH}_3$ ).

20    Step 3

Synthesis of 2-N-{(4,6-bis(N-ethylperfluorooctylsulphonamido)-1,3,5-triazin-2-yl)}-aminoethyl propenoate

2-N-[4,6-bis(N-ethylperfluorooctylsulphonamido)-1,3,5-triazin-2-yl]amino ethanol (11.58, 9.7mmols) and acryloyl chloride (1.32g, 14.6mmols) were dissolved in hot toluene (80mls). Collidine (1.77g, 14.6mmols) was added as a toluene solution (10mls) down the reflux condenser. The resulting reaction mixture was heated under reflux for 2 hours and then filtered hot. Toluene was removed at the pump and the resulting solid dissolved in diethyl ether (400mls). The ethereal solution was washed with 1M HCl (2x50mls) distilled water (2x40mls) and then dried over sodium sulphate. Filtration and evaporation of the solvent at the pump afforded 8.8g (73%) of product.

<sup>1</sup>H NMR (CDCl<sub>3</sub>) δ (ppm) 6.42 (1H, dd, <sup>3</sup>J<sub>H-H</sub> 17.3, 1.3 Hz, CH=CH<sub>2</sub> *trans*), 6.11 (1H, dd, <sup>3</sup>J<sub>H-H</sub> 17.3, 10.5 Hz, CH=CH<sub>2</sub>), 5.88 (2H, m, NH, CH=CH<sub>2</sub> *cis*), 4.32 (2H, t, <sup>3</sup>J<sub>H-H</sub> 5.3 Hz, CH<sub>2</sub>O), 4.13 (4H, m, NCH<sub>2</sub>CH<sub>3</sub>), 3.72 (2H, m, OCH<sub>2</sub>CH<sub>2</sub>N), 1.36  
5 (6H, m, NCH<sub>2</sub>CH<sub>3</sub>).

<sup>13</sup>C{<sup>1</sup>H} NMR (CDCl<sub>3</sub>) δ (ppm) 166.0, 165.6, 164.6, 164.3, (triazine/C=O), 131.5 (C=C), 127.8 (C=C), 62.5 (CH<sub>2</sub>O),  
10 45.4 (CH<sub>3</sub>CH<sub>2</sub>N), 40.5 (CH<sub>2</sub>N), 14.9 (CH<sub>3</sub>CH<sub>2</sub>).

### Example 2

#### Synthesis of 2-[N-methyl-N-((4,6-bis(N-ethylperfluorooctylsulphonamido)-1,3,5-triazin-2-yl))]-aminoethyl propenoate

2-Chloro-4,6-bis(N-ethylperfluorooctylsulphonamido)-1,3,5-triazine (20g, 17.2mmols) was held as a solution/suspension in chloroform (150mls). N,N-Dimethylethylamino acrylate (2.45g, 17.2mmols) was added  
20 dropwise, over a period of 30 minutes, as a chloroform solution (50mls). The reaction mixture was stirred for 3 hours at room temperature. The chloroform solution was filtered through Celite®, concentrated (to a volume of approximately 30mls) and then passed through a short path  
25 column of silica. Product was eluted with chloroform. Evaporation of the solvent afforded 19g (88%) of a sticky oil that crystallised with time (2 days).

<sup>1</sup>H NMR (CDCl<sub>3</sub>) δ (ppm) 6.37 (1H, dd, <sup>3</sup>J<sub>H-H</sub> 17.3, 1.5 Hz, CH=CH<sub>2</sub> *trans*), 6.09 (1H, dd, <sup>3</sup>J<sub>H-H</sub> 17.3, 10.5 Hz, CH=CH<sub>2</sub>), 5.83 (1H, dd, <sup>3</sup>J<sub>H-H</sub> 10.5, 1.5 Hz, CH=CH<sub>2</sub> *cis*), 4.36 (2H, t, <sup>3</sup>J<sub>H-H</sub> 5.6 Hz, CH<sub>2</sub>O), 4.14 (4H, m, NCH<sub>2</sub>CH<sub>3</sub>), 3.86 (2H, t, <sup>3</sup>J<sub>H-H</sub> 5.6 Hz, OCH<sub>2</sub>CH<sub>2</sub>N), 3.20 (3H, s, CH<sub>3</sub>N), 1.38 (6H, m, NCH<sub>2</sub>CH<sub>3</sub>).  
30

$^{13}\text{C}\{^1\text{H}\}$  NMR ( $\text{CDCl}_3$ )  $\delta$  (ppm) 165.8, 164.5, 164.2, 164.0, (triazine/ $\text{C}=\text{O}$ ), 131.3 ( $\text{C}=\text{C}$ ), 127.9 ( $\text{C}=\text{C}$ ), 61.7 ( $\text{CH}_2\text{O}$ ), 48.3 ( $\text{CH}_2\text{N}$ ), 45.5 ( $\text{CH}_2\text{N}$ ), 36.3 ( $\text{CH}_3\text{N}$ ), 15.0 ( $\text{CH}_3\text{CH}_2$ ).

5 Example 3  
Step 1

Synthesis of 2,4-Bis(1H,1H,2H,2H-perfluorooctoxy)-6-chloro-1,3,5-triazine

Lithium hydroxide (0.49g, 11.7mmols) and 1H,1H,2H,2H  
10 perfluorooctanol (5.4g 11.7mmols) were held as a  
solution/suspension in tetrahydrofuran (25mls). Cyanuric  
chloride (1.08g, 5.8mmols) and distilled water (1ml) were  
added and the reaction mixture was stirred at room  
temperature overnight. The resulting solution/suspension  
15 was precipitated into distilled water (200mls) and  
extracted with diethyl ether (2x200mls). The organic  
extract was dried over sodium sulphate, filtered and the  
diethyl ether was removed at the pump. The resulting  
white solid was recrystallised from diethyl ether (50mls),  
20 to afford 3.3g (54%) of product.

$^1\text{H}$  NMR ( $\text{CDCl}_3$ )  $\delta$  (ppm) 4.75 (2H, t,  $^3\text{J}_{\text{H-H}}$  6.6 Hz,  $\text{OCH}_2\text{CH}_2$ ),  
2.63 (2H, tt,  $^3\text{J}_{\text{H-F}}$  18.1 Hz,  $^3\text{J}_{\text{H-H}}$  6.6 Hz  $\text{OCH}_2\text{CH}_2$ ).

25  $^{13}\text{C}\{^1\text{H}\}$  NMR ( $\text{CDCl}_3$ )  $\delta$  (ppm) 173.2, 171.7 (triazine), 61.1  
( $\text{OCH}_2\text{CH}_2$ ), 30.5 (t,  $^2\text{J}_{\text{C-F}}$  22.0 Hz  $\text{OCH}_2\text{CH}_2\text{CF}_2$ ).

Step 2

30 Synthesis of 2-[N-methyl-N-((4,6-bis(1H,1H,2H,2H-perfluorooctoxy)-1,3,5-triazin-2-yl))]-aminoethyl propenoate

2,4-Bis(1H,1H,2H,2H-perfluorooctoxy)-6-chloro-1,3,5-triazine (0.5g, 0.48mmols) was held as a  
solution/suspension in chloroform (10mls). N,N-  
35 Dimethylethyl-amino acrylate (0.076g, 0.53mmols) was  
added dropwise as a neat liquid at room temperature and  
the reaction mixture was stirred for 2 hours. The

chloroform solution was extracted with 2M HCl (2x10mls), distilled water (2x10mls), dried over sodium sulphate and filtered. Evaporation of the solvent afforded 0.48g (90%) of product as a waxy solid.

5

$^1\text{H}$  NMR ( $\text{CDCl}_3$ )  $\delta$  (ppm) 6.30 (1H, d,  $^3J_{\text{H-H}}$  17.2 Hz,  $\text{CH}=\text{CH}_2$  trans), 6.00 (1H, dd,  $^3J_{\text{H-H}}$  17.3, 10.4 Hz,  $\text{CH}=\text{CH}_2$ ), 5.75 (1H, d,  $^3J_{\text{H-H}}$  10.4 Hz,  $\text{CH}=\text{CH}_2$  cis), 4.57 (4H, m,  $\text{CF}_2\text{CH}_2\text{CH}_2\text{O}$ ), 4.31 (2H, t, 5.5 Hz,  $\text{OCH}_2\text{CH}_2\text{N}$ ), 3.84 (2H, t,  $^3J_{\text{H-H}}$  5.5 Hz,  $\text{OCH}_2\text{CH}_2\text{N}$ ), 3.14 (3H, s,  $\text{CH}_3\text{N}$ ), 2.56 (4H, m,  $\text{CF}_2\text{CH}_2\text{CH}_2\text{O}$ ).

10


$^{13}\text{C}\{^1\text{H}\}$  NMR ( $\text{CDCl}_3$ )  $\delta$  (ppm) 171.3, 171.1, 167.3, 165.8, (triazine/ $\text{C}=\text{O}$ ), 131.1 ( $\text{C}=\text{C}$ ), 128.0 ( $\text{C}=\text{C}$ ), 61.8 ( $\text{CH}_2\text{O}$ ), 59.2 ( $\text{CH}_2\text{N}$ ), 48.0 ( $\text{CH}_2\text{N}$ ), 36.1 ( $\text{CH}_3\text{N}$ ), 30.2 (t, 22 Hz,  $\text{CH}_2\text{CF}_2$ ).

15

20

## Claims

1. A compound of formula (I)



(I)

wherein R<sup>1</sup> and R<sup>2</sup> are independently selected from saturated fluorocarbon substituted side chains; R<sup>3</sup> is an unsaturated moiety which may be polymerised, and X is O, S or NR<sup>4</sup> where R<sup>4</sup> is hydrogen or alkyl.

2. A compound according to claim 1 wherein R<sup>1</sup> and R<sup>2</sup> are independently selected from NR<sup>5</sup>(CH<sub>2</sub>)<sub>n</sub>C<sub>m</sub>F<sub>2m+1</sub>, O(CH<sub>2</sub>)<sub>n</sub>C<sub>m</sub>F<sub>2m+1</sub>, S(CH<sub>2</sub>)<sub>n</sub>C<sub>m</sub>F<sub>2m+1</sub>, NR<sup>5</sup>S(O)<sub>2</sub>(CH<sub>2</sub>)<sub>p</sub>C<sub>m</sub>F<sub>2m+1</sub> or CR<sup>5</sup>[CO<sub>2</sub>(CH<sub>2</sub>)<sub>n</sub>C<sub>m</sub>F<sub>2m+1</sub>]<sub>2</sub>, where R<sup>5</sup> is hydrogen or alkyl, n and m are independently an integer of 1-12, and p is 0 or an integer of from 1-12.


3. A compound according to claim 1 or claim 2 wherein R<sup>1</sup> and R<sup>2</sup> are the same.

4. A compound according to any one of the preceding claims wherein R<sup>1</sup> and R<sup>2</sup> are selected from O(CH<sub>2</sub>)<sub>n</sub>C<sub>m</sub>F<sub>2m+1</sub> or NR<sup>5</sup>S(O)<sub>p</sub>(CH<sub>2</sub>)<sub>n</sub>C<sub>m</sub>F<sub>2m+1</sub> where n, m, p and R<sup>5</sup> are as defined in claim 2.

5. A compound according to any one of the preceding claims R<sup>3</sup> is a group of formula -(CH<sub>2</sub>)<sub>q</sub>OC(O)C(R<sup>6</sup>)CR<sup>7</sup>R<sup>8</sup> where q is an integer of from 1 to 12, and R<sup>6</sup>, R<sup>7</sup> and R<sup>8</sup> are independently selected from hydrogen or alkyl such as C<sub>1-4</sub> alkyl.

6. A compound according to claim 5 where  $R^6$ ,  $R^7$  and  $R^8$  are all hydrogen.

7. A method of preparing a compound of formula (I) as defined in claim 1, which method comprises reacting a compound of formula (II)



(II)

where  $R^1$  and  $R^2$  are as defined in claim 1 and  $Y$  is a leaving group, with a group of formula (III)




where  $X$  is as defined in claim 1 and  $R^{3'}$  is a group  $R^3$  as defined in relation to formula (I) or a precursor group which may be reacted to form a group  $R^3$  and  $R^a$  is hydrogen or a lower alkyl group; and thereafter if necessary converting a group  $R^{3'}$  to a group  $R^3$ .

8. A method according to claim 7 wherein  $R^{3'}$  is a group of formula  $(CH_2)_qOH$ , and this is subsequently converted to  $R^3$  by reaction with an acid halide of formula  $ZC(O)C(R^6)CR^7R^8$  where  $Z$  is a halogen and  $R^6$ ,  $R^7$  and  $R^8$  are as defined in claim 5, in the presence of a base.



9. A process for preparing a compound of formula (II) as defined in claim 7 which comprises reacting a compound of formula (IV)




(IV)

where R<sup>1</sup> is as defined in relation to formula (I), Y is as defined in relation to formula (II) and Y' is a leaving group, with a compound of formula (V)




where R<sup>2</sup> is as defined in relation to formula (I), in the presence of a base.

10. A method according to claim 9 wherein the compound of formula (IV) is prepared by reacting a compound of formula (VI)



(VI)

wherein Y, Y' and Y'' are the same or different leaving groups, with a compound of formula (VII)




where  $R^1$  is as defined in claim 1, in the presence of a base.

11. A method according to claim 10 wherein the compound of formula (IV) is converted to a compound of formula (II) in situ.

12. A polymeric compound which has been derived from a compound of formula (I).

13. A polymeric compound according to claim 12 which comprises a polymer or copolymer including repeating units of formula (VIII)




(VIII)

where  $R^1$ ,  $R^2$  and  $X$  are as defined in relation to formula (I),  $t$  is an integer in excess of 5, and  $R^9$  is a saturated derivative of  $R^3$  as defined in relation to formula (I).

14. A polymeric compound according to claim 13 wherein  $XR^9$  is a moiety of formula (IX)

17



(IX)

15. A substrate which is coated with a polymeric compound according to any one of claims 12 to 14.

16. A substrate according to claim 15 which is a fabric.

# INTERNATIONAL SEARCH REPORT

Int lional Application No

PCT/GB 98/02104

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C07D251/70 C08F20/68

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C07D C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

| Category * | Citation of document, with indication, where appropriate, of the relevant passages  | Relevant to claim No. |
|------------|---|-----------------------|
| A          | EP 0 366 884 A (AMERICAN CYANAMID CO)<br>9 May 1990<br>see claims 3,8<br>----   | 1,12                  |
| A          | WO 97 13024 A (SECR DEFENCE ; WILLIS COLIN<br>ROBERT (GB); BREWER STUART ANSON (GB))<br>10 April 1997<br>cited in the application<br>see page 1; claims<br>---- | 1,12,16               |
| A          | GB 1 102 903 A (DAIKIN ) 14 February 1968<br>cited in the application<br>see claims 1,8<br>-----  | 1,12                  |

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

\* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

16 September 1998

Date of mailing of the international search report

24/09/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl.  
Fax: (+31-70) 340-3018

Authorized officer

De Jong, B

# INTERNATIONAL SEARCH REPORT

Information on patent family members


In International Application No

PCT/GB 98/02104

| Patent document<br>cited in search report | Publication<br>date | Patent family<br>member(s) | Publication<br>date |
|---|---------------------|----------------------------|---------------------|
| EP 0366884 A                              | 09-05-1990          | US 5175201 A               | 29-12-1992          |
|   |                     | AT 132493 T                | 15-01-1996          |
|   |                     | CA 1339662 A               | 10-02-1998          |
|   |                     | DE 68925339 D              | 15-02-1996          |
|   |                     | DE 68925339 T              | 01-08-1996          |
|   |                     | JP 2172980 A               | 04-07-1990          |
|   |                     | MX 169828 B                | 27-07-1993          |
|   |                     | NO 302829 B                | 27-04-1998          |
|   |                     | US 5410051 A               | 25-04-1995          |
|   |                     | US 5359014 A               | 25-10-1994          |
| WO 9713024 A                              | 10-04-1997          | EP 0854951 A               | 29-07-1998          |
|   |                     | GB 2318354 A               | 22-04-1998          |
| GB 1102903 A                              |                     | JP 48041152 B              | 05-12-1973          |
|   |                     | CH 253565 A                |                     |
|   |                     | CH 443875 B                |                     |
|   |                     | DE 1494430 A               | 09-10-1969          |
|   |                     | FR 1438617 A               | 29-07-1966          |



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

|   |           |  |
|---|-----------|--|
| <b>(51) International Patent Classification <sup>6</sup> :</b><br><b>C07D 251/70, C08F 20/68</b>  | <b>A1</b> | <b>(11) International Publication Number:</b> <b>WO 99/05127</b><br><b>(43) International Publication Date:</b> 4 February 1999 (04.02.99)   |
| <b>(21) International Application Number:</b> PCT/GB98/02104<br><b>(22) International Filing Date:</b> 16 July 1998 (16.07.98)<br><br><b>(30) Priority Data:</b><br>9715709.3                      26 July 1997 (26.07.97)                      GB<br><br><b>(71) Applicant (for all designated States except US):</b> THE SECRETARY OF STATE FOR DEFENCE [GB/GB]; Defence Evaluation & Research Agency, Ively Road, Farnborough, Hampshire GU14 0LX (GB).<br><br><b>(72) Inventors; and</b><br><b>(75) Inventors/Applicants (for US only):</b> WILLIS, Colin, Robert [GB/GB]; CBD Porton Down, Salisbury, Wiltshire SP4 0JQ (GB). BREWER, Stuart, Anson [GB/GB]; CBD Porton Down, Salisbury, Wiltshire SP4 0JQ (GB). JONES, Brian, George [GB/GB]; CBD Porton Down, Salisbury, Wiltshire SP4 0JQ (GB).<br><br><b>(74) Agent:</b> BOWDERY, A., O.; D/IPR, Formalities Section, Poplar 2, MOD Abbey Wood #19, Bristol BS34 8JH (GB).   |           | <b>(81) Designated States:</b> AU, CA, CN, GB, JP, KR, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).<br><br><b>Published</b><br><i>With international search report.</i> |
| <b>(54) Title:</b> FLUORINATED TRIAZINE MONOMERS<br><br><b>(57) Abstract</b><br><p>A compound of formula (I), wherein R<sup>1</sup> and R<sup>2</sup> are independently selected from saturated fluorocarbon substituted side chains, such as NR<sup>5</sup>(CH<sub>2</sub>)<sub>n</sub>C<sub>m</sub>F<sub>2m+1</sub>, O(CH<sub>2</sub>)<sub>n</sub>C<sub>m</sub>F<sub>2m+1</sub>, S(CH<sub>2</sub>)<sub>n</sub>C<sub>m</sub>F<sub>2m+1</sub>, NR<sup>5</sup>S(O)<sub>2</sub>(CH<sub>2</sub>)<sub>p</sub>C<sub>m</sub>F<sub>2m+1</sub>, or CR<sup>5</sup>[CO<sub>2</sub>(CH<sub>2</sub>)<sub>n</sub>C<sub>m</sub>F<sub>2m+1</sub>]<sub>2</sub>, where R<sup>5</sup> is hydrogen or alkyl, n and m are independently an integer of 1-12, and p is 0 or an integer of 1-12, R<sup>3</sup> is an unsaturated moiety which may be polymerised, and X is O, S or NR<sup>4</sup> where R<sup>4</sup> is hydrogen or alkyl, as well as methods for the preparation of these compounds. Compounds of formula (I) are useful monomers in the preparation of oil- and water-repellent polymers.</p> <div style="text-align: center;">  <p>(I)</p> </div> |           |  |

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

|    |                          |    |  |    |  |    |                          |
|----|--------------------------|----|--|----|--|----|--------------------------|
| AL | Albania                  | ES | Spain                                    | LS | Lesotho                                      | SI | Slovenia                 |
| AM | Armenia                  | FI | Finland                                  | LT | Lithuania                                    | SK | Slovakia                 |
| AT | Austria                  | FR | France                                   | LU | Luxembourg                                   | SN | Senegal                  |
| AU | Australia                | GA | Gabon                                    | LV | Latvia                                       | SZ | Swaziland                |
| AZ | Azerbaijan               | GB | United Kingdom                           | MC | Monaco                                       | TD | Chad                     |
| BA | Bosnia and Herzegovina   | GE | Georgia                                  | MD | Republic of Moldova                          | TG | Togo                     |
| BB | Barbados                 | GH | Ghana                                    | MG | Madagascar                                   | TJ | Tajikistan               |
| BE | Belgium                  | GN | Guinea                                   | MK | The former Yugoslav<br>Republic of Macedonia | TM | Turkmenistan             |
| BF | Burkina Faso             | GR | Greece                                   |    |  | TR | Turkey                   |
| BG | Bulgaria                 | HU | Hungary                                  | ML | Mali   | TT | Trinidad and Tobago      |
| BJ | Benin                    | IE | Ireland                                  | MN | Mongolia                                     | UA | Ukraine                  |
| BR | Brazil                   | IL | Israel                                   | MR | Mauritania                                   | UG | Uganda                   |
| BY | Belarus                  | IS | Iceland                                  | MW | Malawi                                       | US | United States of America |
| CA | Canada                   | IT | Italy                                    | MX | Mexico                                       | UZ | Uzbekistan               |
| CF | Central African Republic | JP | Japan                                    | NE | Niger  | VN | Viet Nam                 |
| CG | Congo                    | KE | Kenya                                    | NL | Netherlands                                  | YU | Yugoslavia               |
| CH | Switzerland              | KG | Kyrgyzstan                               | NO | Norway                                       | ZW | Zimbabwe                 |
| CI | Côte d'Ivoire            | KP | Democratic People's<br>Republic of Korea | NZ | New Zealand                                  |    |                          |
| CM | Cameroon                 | KR | Republic of Korea                        | PL | Poland                                       |    |                          |
| CN | China                    | KZ | Kazakhstan                               | PT | Portugal                                     |    |                          |
| CU | Cuba                     | LC | Saint Lucia                              | RO | Romania                                      |    |                          |
| CZ | Czech Republic           | LI | Liechtenstein                            | RU | Russian Federation                           |    |                          |
| DE | Germany                  | LK | Sri Lanka                                | SD | Sudan  |    |                          |
| DK | Denmark                  | LR | Liberia                                  | SE | Sweden                                       |    |                          |
| EE | Estonia                  |    |  | SG | Singapore                                    |    |                          |

## FLUORINATED TRIAZINE MONOMERS

The present invention relates to novel monomeric compounds which can be used in the production of polymers which have a high degree of oil and water-repellency and which may be fixed to substrates such as clothing, to processes for their preparation and to polymers produced therefrom.

Oil- and water- repellent treatments are in widespread use, in particular for outdoor clothing applications, sportswear, leisurewear and in military applications. These treatments generally require the incorporation of a fluoropolymer into or more particularly, fixed onto the surface of the clothing fabric. The degree of oil and water repellency is a function of the number of fluorocarbon groups or moieties that can be fitted into the available space. The greater the concentration of such moieties, the greater the repellency of the finish.

In addition however, the polymeric compounds must be able to form durable bonds with the substrate. Oil-and water-repellent textile treatments are generally based on fluoropolymers that are applied to fabric in the form of an aqueous emulsion. The fabric remains breathable and permeable to air since the treatment simply coats the fibres with a very thin, liquid-repellent film. In order to make these finishes durable, they are sometimes co-applied with cross-linking resins that bind the fluoropolymer treatment to fibres. Whilst good levels of durability towards laundering and dry-cleaning can be achieved in this way, the cross-linking resins can seriously damage cellulosic fibres and reduce the mechanical strength of the material.




WO 97/13024 discloses a group of fibre reactive polymers, which include a functional group such as a triazine group, which binds the polymer to the material substrate.

- 5 British patent No 1,102,903 describes certain fluoro alkyl containing compounds which are used in water- and oil-repellent compositions.

The applicants have produced certain novel monomers,  
10 which give rise to polymers which have a high number of fluorocarbon substituents per monomer unit.

The present invention provides a compound of formula (I)



- wherein R<sup>1</sup> and R<sup>2</sup> are independently selected from saturated fluorocarbon substituted side chains;  
20 R<sup>3</sup> is an unsaturated moiety which may be polymerised, and X is O, S or NR<sup>4</sup> where R<sup>4</sup> is hydrogen or alkyl.

As used herein, the term "alkyl" refers to straight or branched chain alkyl or cycloalkyl groups, in particular  
25 those having from 1 to 12 and preferably from 1 to 6 carbon atoms. The term "saturated" refers to groups which do not contain carbon-carbon double bonds. Conversely the term "unsaturated" refers to groups which include carbon-carbon double bonds.

30


Suitable fluorocarbon substituted side chains for R<sup>1</sup> and/or R<sup>2</sup> include groups which are hydrophobic groups

which are able to confer water- and/or oil- repellency on the resultant polymer. In particular  $R^1$  and  $R^2$  are independently selected from  $NR^5(CH_2)_nC_mF_{2m+1}$ ,  $O(CH_2)_nC_mF_{2m+1}$ ,  $S(CH_2)_nC_mF_{2m+1}$ ,  $NR^5S(O)_2(CH_2)_pC_mF_{2m+1}$  or  $CR^5[CO_2(CH_2)_nC_mF_{2m+1}]_2$ , where  $R^5$  is hydrogen or alkyl, and  $n$  and  $m$  are independently an integer of 1-12, and  $p$  is 0 or an integer of from 1-12.

Conveniently  $R^1$  and  $R^2$  are the same. They are preferably selected from  $O(CH_2)_nC_mF_{2m+1}$  or  $NR^5S(O)_2(CH_2)_pC_mF_{2m+1}$ . Suitably  $R^5$  is methyl, ethyl or n-propyl, in particular ethyl. Preferred integers for  $n$  and  $p$  are from 1-3, suitably 2, whilst preferred integers for  $m$  are from 6 to 10, most preferably 8.


Suitable polymerisable groups  $R^3$  are alkenes or alkynes which may also include a functional group such as an acyloxy group. Particularly preferred groups for  $R^3$  are groups of formula  $(CH_2)_qOC(O)C(R^6)CR^7R^8$  where  $q$  is an integer of from 1 to 12, suitably from 1 to 4 and especially 2, and  $R^6$ ,  $R^7$  and  $R^8$  are independently selected from hydrogen or alkyl such as  $C_{1-4}$  alkyl. Preferably  $R^6$ ,  $R^7$  and  $R^8$  are all hydrogen.

Compounds of formula (I) are suitably prepared by reacting a compound of formula (II)



(II)

where  $R^1$  and  $R^2$  are as defined in relation to formula (I) and  $Y$  is a leaving group, with a group of formula (III)



(III)

where X is as defined in relation to formula (I) and R<sup>3'</sup>  
5 is a group R<sup>3</sup> as defined in relation to formula (I) or a  
precursor group which may be reacted to form a group R<sup>3</sup>  
and R<sup>a</sup> is hydrogen or alkyl; and thereafter if necessary  
converting a precursor group R<sup>3'</sup> to a group R<sup>3</sup>.

10 Preferably R<sup>a</sup> is hydrogen or a lower alkyl, for example a  
C<sub>1-3</sub> alkyl, in particular methyl.

Suitable leaving groups for Y include halogen such as  
fluorine and chlorine, in particular chlorine, or amine  
15 leaving groups such as substituted pyridines for instance  
nicotinic acid or colladine.

The reaction is suitably effected in an organic solvent  
such as tetrahydrofuran (THF), acetone, toluene or  
20 chloroform. It may be effected at temperatures of from  
0 to 200°C, suitably from 25 to 150°C, depending upon the  
precise nature of the reactants and solvents involved.  
Conveniently the reaction may be effected at room  
temperature or under reflux conditions.


25 Preferably the reaction is effected under basic  
conditions. Weak bases may suffice, and in some  
instances, the compound of formula (III) may itself act  
as an acid scavenger and so the use of an excess,  
30 particularly a 2 molar excess of the compound of formula  
(III) will ensure that that the reaction proceeds  
effectively.

Suitable groups R<sup>3'</sup> which are precursor groups to R<sup>3</sup> would  
35 be apparent to the skilled person. For example, where  
R<sup>3</sup> is a group (CH<sub>2</sub>)<sub>q</sub>OC(O)C(R<sup>6</sup>)CR<sup>7</sup>R<sup>8</sup>, a suitable precursor  
group R<sup>3</sup> would be (CH<sub>2</sub>)<sub>q</sub>OH, which can be readily converted

to  $R^3$  by reaction with a suitable acid halide for example an acid chloride of formula  $ClC(O)C(R^6)CR^7R^8$  in the presence of a base, such as a weak base, for example pyridine or a pyridine derivative such as collidine.

- 5 This reaction is suitably effected in an organic solvent such as toluene at elevated temperatures, conveniently at the reflux temperature of the solvent.

Certain compounds of formula (II) are known (see for  
10 example British Patent No. 1,102,903). These compounds can be prepared by reacting a compound of formula (IV)



(IV)

15

where  $R^1$  is as defined in relation to formula (I), Y is as defined in relation to formula (II) and  $Y'$  is a leaving group,  
with a compound of formula (V)

20



where  $R^2$  is as defined in relation to formula (I), in the presence of a base.

25

Suitable bases are those which react with a compound of formula (V) so as to produce a nucleophilic moiety of formula (V')


30



Thus the selection of suitable bases will depend upon the precise nature of the group  $R^2$  and will be readily understood or determinable by the skilled person. For example, where  $R^2$  is a group  $O(CH_2)_n C_m F_{2m+1}$ , strong bases such as alkali metal hydroxides, in particular lithium hydroxide, may be used. Alternatively, where  $R^2$  is a group  $NR^5 S(O)_2 (CH_2)_p C_m F_{2m+1}$ , stronger bases such as alkali metal alkoxides, in particular sodium or potassium methoxide or ethoxide may be used.

10

Compounds of formula (IV) are suitably prepared by reacting a compound of formula (VI)



15

(VI)

wherein Y, Y' and Y'' are the same or different leaving groups, with a compound of formula (VII)

20

 $R^1H$ 

(VII)

25

where  $R^1$  is as defined in relation to formula (I), in the presence of a base.

Reaction conditions will be generally similar to those described above in relation to the reaction between compounds of formula (IV) and formula (V).

30


Where compounds of formula (V) and formula (VII) are the same, compounds of formula (II) may be prepared directly in one pot. If necessary, the reaction can be controlled

in a stepwise manner in order to maximise yield of the target compound by controlling the reaction temperature. For example, where  $R^1$  and  $R^2$  are groups of formula  $NR^5S(O)_2(CH_2)_nC_mF_{2m+1}$ , the compound of formula (IV) may be prepared at depressed temperatures, for example at about -78°C. Allowing the reaction mixture to warm up to approximately 0°C will produce a compound of formula (II) after suitable work-up.

Compounds of formula (III), (V), (VI) and (VII) are either known compounds or they can be prepared from known compounds using conventional methods. A preferred compound of formula (VI) is cyanuric chloride.


Compounds of formula (I) may be polymerised or copolymerised using conventional technology, e.g emulsion polymerisation.

Polymers or copolymers including units of formula (VIII)



(VIII)

where  $R^1$ ,  $R^2$  and  $X$  are as defined in relation to formula (I),  $t$  is an integer in excess of 5, and  $R^9$  is a saturated derivative of  $R^3$  as defined in relation to formula (I) form a preferred embodiment of the invention. In particular  $XR^9$  will be a moiety of formula (IX)



(IX)

Suitably the monomers of the invention are copolymerised with a monomer which comprises a fibre reactive moiety  
 5 for example as described in WO 97/13024.

The invention will now be particularly described by way of example.

#### 10 Example 1

##### Step 1

##### Synthesis of 2-chloro-4,6-bis(N-ethylperfluorooctylsulphonamido)-1,3,5-triazine

Metallic sodium (4.08g, 177mmols) was reacted with  
 15 methanol (150mls). N-Ethyl perfluorooctyl sulphonamide (93.28g, 177mmols) was added, and the resulting solution was stirred for 30 minutes. The methanol was removed at the pump (a vacuum pump was required to remove the final traces of solvent). The resulting sticky solid was  
 20 dissolved in acetone (300mls) and cooled to -65°C under argon. Recrystallised cyanuric chloride (16.33g, 88.5mmols) dissolved in acetone (100mls) was added to the reaction mixture dropwise such that the temperature did not rise above -50°C (~1hour). After the addition, the  
 25 reaction mixture was allowed to slowly warm to room temperature (1 hour) and then stirred for a further 3 hours. The precipitated solid was removed by filtration and dried under vacuum. Purification by soxhlet extraction with acetone afforded 61g (56.9%) of a fine white powder.

30

<sup>1</sup>H NMR (CDCl<sub>3</sub>) δ (ppm) 4.20 (2H, q, <sup>3</sup>J<sub>H-H</sub> 6.8 Hz, CH<sub>2</sub>CH<sub>3</sub>), 1.40 (3H, t, <sup>3</sup>J<sub>H-H</sub> 6.8 Hz, CH<sub>2</sub>CH<sub>3</sub>).

$^{13}\text{C}\{^1\text{H}\}$  NMR ( $\text{CDCl}_3$ )  $\delta$  (ppm) 171.3, 165.0 (triazine), 46.3 ( $\text{CH}_2\text{CH}_3$ ), 14.5 ( $\text{CH}_2\text{CH}_3$ ).

5 Step 2

Synthesis of 2-N-{4,6-bis(N-ethylperfluorooctylsulphonamido)-1,3,5-triazin-2-yl}-amino ethanol

A THF solution (85mls) of 2-chloro-4,6-bis(N-ethylperfluorooctylsulphonamido)-1,3,5-triazine (15g, 12.9mmols) and ethanolamine (1.6g, 26.2mmols) were heated under reflux for 1 hour. The hot solution/suspension was filtered and the product was allowed to crystallise overnight to afford 12.8g (83%) of product.

15

$^1\text{H}$  NMR ( $\text{d}_6$  acetone)  $\delta$  (ppm) 4.85 (4H, m,  $\text{NCH}_2\text{CH}_3$ ), 4.38 (2H, t,  $^3\text{J}_{\text{H-H}}$  5 Hz,  $\text{CH}_2\text{O}$ ), 4.22 (2H, dt, 5, 5 Hz,  $\text{OCH}_2\text{CH}_2\text{N}$ ), 2.05 (6H, m  $\text{NCH}_2\text{CH}_3$ ).

20 Step 3

Synthesis of 2-N-{(4,6-bis(N-ethylperfluorooctylsulphonamido)-1,3,5-triazin-2-yl)}-aminoethyl propenoate

2-N-[4,6-bis(N-ethylperfluorooctylsulphonamido)-1,3,5-triazin-2-yl]amino ethanol (11.58, 9.7mmols) and acryloyl chloride (1.32g, 14.6mmols) were dissolved in hot toluene (80mls). Collidine (1.77g, 14.6mmols) was added as a toluene solution (10mls) down the reflux condenser. The resulting reaction mixture was heated under reflux for 2 hours and then filtered hot. Toluene was removed at the pump and the resulting solid dissolved in diethyl ether (400mls). The ethereal solution was washed with 1M HCl (2x50mls) distilled water (2x40mls) and then dried over sodium sulphate. Filtration and evaporation of the solvent at the pump afforded 8.8g (73%) of product.



<sup>1</sup>H NMR (CDCl<sub>3</sub>) δ (ppm) 6.42 (1H, dd, <sup>3</sup>J<sub>H-H</sub> 17.3, 1.3 Hz, CH=CH<sub>2</sub> *trans*), 6.11 (1H, dd, <sup>3</sup>J<sub>H-H</sub> 17.3, 10.5 Hz, CH=CH<sub>2</sub>), 5.88 (2H, m, NH, CH=CH<sub>2</sub> *cis*), 4.32 (2H, t, <sup>3</sup>J<sub>H-H</sub> 5.3 Hz, CH<sub>2</sub>O), 4.13 (4H, m, NCH<sub>2</sub>CH<sub>3</sub>), 3.72 (2H, m, OCH<sub>2</sub>CH<sub>2</sub>N), 1.36 (6H, m, NCH<sub>2</sub>CH<sub>3</sub>).

<sup>13</sup>C{<sup>1</sup>H} NMR (CDCl<sub>3</sub>) δ (ppm) 166.0, 165.6, 164.6, 164.3, (triazine/C=O), 131.5 (C=C), 127.8 (C=C), 62.5 (CH<sub>2</sub>O), 45.4 (CH<sub>3</sub>CH<sub>2</sub>N), 40.5 (CH<sub>2</sub>N), 14.9 (CH<sub>3</sub>CH<sub>2</sub>).

### Example 2

#### Synthesis of 2-[N-methyl-N-((4,6-bis(N-ethylperfluorooctylsulphonamido)-1,3,5-triazin-2-yl))]-aminoethyl propenoate

2-Chloro-4,6-bis(N-ethylperfluorooctylsulphonamido)-1,3,5-triazine (20g, 17.2mmols) was held as a solution/suspension in chloroform (150mls). N,N-Dimethylethylamino acrylate (2.45g, 17.2mmols) was added dropwise, over a period of 30 minutes, as a chloroform solution (50mls). The reaction mixture was stirred for 3 hours at room temperature. The chloroform solution was filtered through Celite®, concentrated (to a volume of approximately 30mls) and then passed through a short path column of silica. Product was eluted with chloroform. Evaporation of the solvent afforded 19g (88%) of a sticky oil that crystallised with time (2 days).

<sup>1</sup>H NMR (CDCl<sub>3</sub>) δ (ppm) 6.37 (1H, dd, <sup>3</sup>J<sub>H-H</sub> 17.3, 1.5 Hz, CH=CH<sub>2</sub> *trans*), 6.09 (1H, dd, <sup>3</sup>J<sub>H-H</sub> 17.3, 10.5 Hz, CH=CH<sub>2</sub>), 5.83 (1H, dd, <sup>3</sup>J<sub>H-H</sub> 10.5, 1.5 Hz, CH=CH<sub>2</sub> *cis*), 4.36 (2H, t, <sup>3</sup>J<sub>H-H</sub> 5.6 Hz, CH<sub>2</sub>O), 4.14 (4H, m, NCH<sub>2</sub>CH<sub>3</sub>), 3.86 (2H, t, <sup>3</sup>J<sub>H-H</sub> 5.6 Hz, OCH<sub>2</sub>CH<sub>2</sub>N), 3.20 (3H, s, CH<sub>3</sub>N), 1.38 (6H, m, NCH<sub>2</sub>CH<sub>3</sub>).

$^{13}\text{C}\{^1\text{H}\}$  NMR ( $\text{CDCl}_3$ )  $\delta$  (ppm) 165.8, 164.5, 164.2, 164.0, (triazine/C=O), 131.3 (C=C), 127.9 (C=C), 61.7 ( $\text{CH}_2\text{O}$ ), 48.3 ( $\text{CH}_2\text{N}$ ), 45.5 ( $\text{CH}_2\text{N}$ ), 36.3 ( $\text{CH}_3\text{N}$ ), 15.0 ( $\text{CH}_3\text{CH}_2$ ).

5 Example 3  
Step 1

Synthesis of 2,4-Bis(1H,1H,2H,2H-perfluorooctoxy)-6-chloro-1,3,5-triazine

Lithium hydroxide (0.49g, 11.7mmols) and 1H,1H,2H,2H  
10 perfluorooctanol (5.4g 11.7mmols) were held as a  
solution/suspension in tetrahydrofuran (25mls). Cyanuric  
chloride (1.08g, 5.8mmols) and distilled water (1ml) were  
added and the reaction mixture was stirred at room  
temperature overnight. The resulting solution/suspension  
15 was precipitated into distilled water (200mls) and  
extracted with diethyl ether (2x200mls). The organic  
extract was dried over sodium sulphate, filtered and the  
diethyl ether was removed at the pump. The resulting  
white solid was recrystallised from diethyl ether (50mls),  
20 to afford 3.3g (54%) of product.

$^1\text{H}$  NMR ( $\text{CDCl}_3$ )  $\delta$  (ppm) 4.75 (2H, t,  $^3J_{\text{H-H}}$  6.6 Hz,  $\text{OCH}_2\text{CH}_2$ ),  
2.63 (2H, tt,  $^3J_{\text{H-F}}$  18.1 Hz,  $^3J_{\text{H-H}}$  6.6 Hz  $\text{OCH}_2\text{CH}_2$ ).

25  $^{13}\text{C}\{^1\text{H}\}$  NMR ( $\text{CDCl}_3$ )  $\delta$  (ppm) 173.2, 171.7 (triazine), 61.1  
( $\text{OCH}_2\text{CH}_2$ ), 30.5 (t,  $^2J_{\text{C-F}}$  22.0 Hz  $\text{OCH}_2\text{CH}_2\text{CF}_2$ ).

Step 2

30 Synthesis of 2-[N-methyl-N-((4,6-bis(1H,1H,2H,2H-perfluorooctoxy)-1,3,5-triazin-2-yl))]-aminoethyl propenoate

2,4-Bis(1H,1H,2H,2H-perfluorooctoxy)-6-chloro-1,3,5-triazine (0.5g, 0.48mmols) was held as a  
solution/suspension in chloroform (10mls). N,N-  
35 Dimethylethyl-amino acrylate (0.076g, 0.53mmols) was  
added dropwise as a neat liquid at room temperature and  
the reaction mixture was stirred for 2 hours. The

chloroform solution was extracted with 2M HCl (2x10mls), distilled water (2x10mls), dried over sodium sulphate and filtered. Evaporation of the solvent afforded 0.48g (90%) of product as a waxy solid.

5

$^1\text{H}$  NMR ( $\text{CDCl}_3$ )  $\delta$  (ppm) 6.30 (1H, d,  $^3J_{\text{H-H}}$  17.2 Hz,  $\text{CH}=\text{CH}_2$  trans), 6.00 (1H, dd,  $^3J_{\text{H-H}}$  17.3, 10.4 Hz,  $\text{CH}=\text{CH}_2$ ), 5.75 (1H, d,  $^3J_{\text{H-H}}$  10.4 Hz,  $\text{CH}=\text{CH}_2$  cis), 4.57 (4H, m,  $\text{CF}_2\text{CH}_2\text{CH}_2\text{O}$ ), 4.31 (2H, t, 5.5 Hz,  $\text{OCH}_2\text{CH}_2\text{N}$ ), 3.84 (2H, t,  $^3J_{\text{H-H}}$  5.5 Hz,  $\text{OCH}_2\text{CH}_2\text{N}$ ), 3.14 (3H, s,  $\text{CH}_3\text{N}$ ), 2.56 (4H, m,  $\text{CF}_2\text{CH}_2\text{CH}_2\text{O}$ ).

10


$^{13}\text{C}\{^1\text{H}\}$  NMR ( $\text{CDCl}_3$ )  $\delta$  (ppm) 171.3, 171.1, 167.3, 165.8, (triazine/ $\text{C}=\text{O}$ ), 131.1 ( $\text{C}=\text{C}$ ), 128.0 ( $\text{C}=\text{C}$ ), 61.8 ( $\text{CH}_2\text{O}$ ), 59.2 ( $\text{CH}_2\text{N}$ ), 48.0 ( $\text{CH}_2\text{N}$ ), 36.1 ( $\text{CH}_3\text{N}$ ), 30.2 (t, 22 Hz,  $\text{CH}_2\text{CF}_2$ ).

15

20

## Claims

1. A compound of formula (I)



(I)

wherein R<sup>1</sup> and R<sup>2</sup> are independently selected from saturated fluorocarbon substituted side chains; R<sup>3</sup> is an unsaturated moiety which may be polymerised, and X is O, S or NR<sup>4</sup> where R<sup>4</sup> is hydrogen or alkyl.

2. A compound according to claim 1 wherein R<sup>1</sup> and R<sup>2</sup> are independently selected from NR<sup>5</sup>(CH<sub>2</sub>)<sub>n</sub>C<sub>m</sub>F<sub>2m+1</sub>, O(CH<sub>2</sub>)<sub>n</sub>C<sub>m</sub>F<sub>2m+1</sub>, S(CH<sub>2</sub>)<sub>n</sub>C<sub>m</sub>F<sub>2m+1</sub>, NR<sup>5</sup>S(O)<sub>2</sub>(CH<sub>2</sub>)<sub>p</sub>C<sub>m</sub>F<sub>2m+1</sub> or CR<sup>5</sup>[CO<sub>2</sub>(CH<sub>2</sub>)<sub>n</sub>C<sub>m</sub>F<sub>2m+1</sub>]<sub>2</sub>, where R<sup>5</sup> is hydrogen or alkyl, n and m are independently an integer of 1-12, and p is 0 or an integer of from 1-12.


3. A compound according to claim 1 or claim 2 wherein R<sup>1</sup> and R<sup>2</sup> are the same.

4. A compound according to any one of the preceding claims wherein R<sup>1</sup> and R<sup>2</sup> are selected from O(CH<sub>2</sub>)<sub>n</sub>C<sub>m</sub>F<sub>2m+1</sub> or NR<sup>5</sup>S(O)<sub>p</sub>(CH<sub>2</sub>)<sub>n</sub>C<sub>m</sub>F<sub>2m+1</sub> where n, m, p and R<sup>5</sup> are as defined in claim 2.

5. A compound according to any one of the preceding claims R<sup>3</sup> is a group of formula -(CH<sub>2</sub>)<sub>q</sub>OC(O)C(R<sup>6</sup>)CR<sup>7</sup>R<sup>8</sup> where q is an integer of from 1 to 12, and R<sup>6</sup>, R<sup>7</sup> and R<sup>8</sup> are independently selected from hydrogen or alkyl such as C<sub>1-4</sub> alkyl.

6. A compound according to claim 5 where  $R^6$ ,  $R^7$  and  $R^8$  are all hydrogen.

7. A method of preparing a compound of formula (I) as defined in claim 1, which method comprises reacting a compound of formula (II)



(II)

where  $R^1$  and  $R^2$  are as defined in claim 1 and  $Y$  is a leaving group, with a group of formula (III)




(III)

where  $X$  is as defined in claim 1 and  $R^{3'}$  is a group  $R^3$  as defined in relation to formula (I) or a precursor group which may be reacted to form a group  $R^3$  and  $R^a$  is hydrogen or a lower alkyl group; and thereafter if necessary converting a group  $R^{3'}$  to a group  $R^3$ .

8. A method according to claim 7 wherein  $R^{3'}$  is a group of formula  $(CH_2)_qOH$ , and this is subsequently converted to  $R^3$  by reaction with an acid halide of formula  $ZC(O)C(R^6)CR^7R^8$  where  $Z$  is a halogen and  $R^6$ ,  $R^7$  and  $R^8$  are as defined in claim 5, in the presence of a base.

9. A process for preparing a compound of formula (II) as defined in claim 7 which comprises reacting a compound of formula (IV)




where R<sup>1</sup> is as defined in relation to formula (I), Y is as defined in relation to formula (II) and Y' is a leaving group, with a compound of formula (V)



where R<sup>2</sup> is as defined in relation to formula (I), in the presence of a base.

10. A method according to claim 9 wherein the compound of formula (IV) is prepared by reacting a compound of formula (VI)



wherein Y, Y' and Y'' are the same or different leaving groups, with a compound of formula (VII)




where  $R^1$  is as defined in claim 1, in the presence of a base.

11. A method according to claim 10 wherein the compound of formula (IV) is converted to a compound of formula (II) in situ.

12. A polymeric compound which has been derived from a compound of formula (I).

13. A polymeric compound according to claim 12 which comprises a polymer or copolymer including repeating units of formula (VIII)




(VIII)

where  $R^1$ ,  $R^2$  and  $X$  are as defined in relation to formula (I),  $t$  is an integer in excess of 5, and  $R^9$  is a saturated derivative of  $R^3$  as defined in relation to formula (I).

14. A polymeric compound according to claim 13 wherein  $XR^9$  is a moiety of formula (IX)

17



(IX)

15. A substrate which is coated with a polymeric compound according to any one of claims 12 to 14.
16. A substrate according to claim 15 which is a fabric.



# INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 98/02104

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C07D251/70 C08F20/68

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C07D C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

| Category * | Citation of document, with indication, where appropriate, of the relevant passages  | Relevant to claim No. |
|------------|---|-----------------------|
| A          | EP 0 366 884 A (AMERICAN CYANAMID CO)<br>9 May 1990<br>see claims 3,8<br>----   | 1,12                  |
| A          | WO 97 13024 A (SECR DEFENCE ; WILLIS COLIN<br>ROBERT (GB); BREWER STUART ANSON (GB))<br>10 April 1997<br>cited in the application<br>see page 1; claims<br>---- | 1,12,16               |
| A          | GB 1 102 903 A (DAIKIN ) 14 February 1968<br>cited in the application<br>see claims 1,8<br>-----  | 1,12                  |

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

16 September 1998

Date of mailing of the international search report

24/09/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3018

Authorized officer

De Jong, B

# INTERNATIONAL SEARCH REPORT

Information on patent family members

In tional Application No

PCT/GB 98/02104

| Patent document<br>cited in search report | Publication<br>date | Patent family<br>member(s) | Publication<br>date |
|---|---------------------|----------------------------|---------------------|
| EP 0366884 A                              | 09-05-1990          | US 5175201 A               | 29-12-1992          |
|   |                     | AT 132493 T                | 15-01-1996          |
|   |                     | CA 1339662 A               | 10-02-1998          |
|   |                     | DE 68925339 D              | 15-02-1996          |
|   |                     | DE 68925339 T              | 01-08-1996          |
|   |                     | JP 2172980 A               | 04-07-1990          |
|   |                     | MX 169828 B                | 27-07-1993          |
|   |                     | NO 302829 B                | 27-04-1998          |
|   |                     | US 5410051 A               | 25-04-1995          |
|   |                     | US 5359014 A               | 25-10-1994          |
| WO 9713024 A                              | 10-04-1997          | EP 0854951 A               | 29-07-1998          |
|   |                     | GB 2318354 A               | 22-04-1998          |
| GB 1102903 A                              |                     | JP 48041152 B              | 05-12-1973          |
|   |                     | CH 253565 A                |                     |
|   |                     | CH 443875 B                |                     |
|   |                     | DE 1494430 A               | 09-10-1969          |
|   |                     | FR 1438617 A               | 29-07-1966          |